



## **Methodology**

### **Kneller Hall Main Hall Coat of Arms**

Take tracings, photographs and notes on existing crest for painting reference. Remove any loose surface material, filling as required to any damaged areas using Toupret filler and making good surface ready for painting.

Apply stabilising base coat at a ratio of 50/50 Dulux Weathershield - colour 30yy 78/018 to entire surface. Apply a second undiluted coat to entire surface.

Apply two further coats of specific colours to specific areas as per client specification, ensuring crisp accurate painting throughout.

GOLD - Apply Ardenbrite Quick Drying Base Coat to all areas to be painted in gold, tinted to an ochre base. Apply 2 to 3 coats Ardenbrite Metallic Paint col: Green Gold until depth of gold colour is reached.

(Dust a very small touch of Cornellisens gold powder to the tops of raised areas of relief to highlight and replicate gold leaf glow).

Apply 2 coats Ardenbrite Protective Glaze to finish.